



ASPHALT COATING

The Asphaltic Coating provides excellent adhesion, moisture resistance, limited protection for bare iron surfaces and is mostly used as a surface sealant.

General Specifications

Material	:	Asphaltic coating per ANSI/AWWA C104/A21.4, NSF-61 & 372 Modified Asphaltic Emulsion, Waterborne Safe, Single Component	
Requirements	:	NSF-61 & 372, ANSI/AWWA C110/A21.10, ANSI/AWWA C111/A21.11, ANSI/AWWA C153/A21.53	
Technical Data	:	Color	: Black,
		Gloss	: Semigloss - non-tacky
		Application	: Spray
		Film Thickness	: Wet: 5 mils Dry: 3 mils
		Dry Time @ 70°F	: 10 min (non-tacky)
		Minimum Dry Time (for Potable Water)	: 7 Days
		Solids	: 60-63%
		VOCs	: 0 - VOC Free
		HAPs	: 0 - HAP Free
		Odor	: None
		Flash Point	: None
		Specific Gravity 20°C	: 1.03 -1.3