



ASPHALT COATING

The Asphaltic Coating provides excellent adhesion, moisture resistance, limited protection for bare iron surfaces and is mostly used as a surface sealant.

General Specifications

Material	:	Asphaltic coating per ANSI/AWWA C104/A21.4, NSF-61 & 372 Modified Asphaltic Emulsion, Waterborne Safe, Single Component		
Requirements	:	NSF-61 & 372, ANSI/AWWA C110/A21.10, ANSI/AWWA C111/A21.11, ANSI/AWWA C153/A21.53		
Technical Data	:	Color	:	Black,
		Gloss	:	Semigloss - non-tacky
		Application	:	Spray
		Film Thickness	:	Wet: 4 mils Dry: 2 mils
		Dry Time @ 70°F	:	10 min (non-tacky)
		Minimum Dry Time (for Potable Water)	:	7 Days
		Solids	:	60-63%
		VOCs	:	0 - VOC Free
		HAPs	:	0 - HAP Free
		Odor	:	None
		Flash Point	:	None
		Specific Gravity 20°C	:	1.03 -1.3